

# PE Pöppelmann 12P15nc

Materialnummer / Material number:	1415001A001PP1
Hersteller / Manufacturer:	Pöppelmann
Typ / Type:	PE-Blend
Bemerkung:	PE-Blend bestehend aus PCR-PE Regranulat auf Basis PE-LLD (1415001M48) und PE-LD Neuware (1115002A001S)
Description:	PE blend consisting of PCR-PE regranulate based on PE-LLD (1415001A001M48) and PE-LD virgin material (1115002A001S)

	Mittelwert	Einheit	Norm
	Average	Unit	Norm
Dichtemessung Dichtemessung			
Dichte [g/cm <sup>3</sup> ] Density	0.916	g/cm <sup>3</sup>	DIN EN ISO 1183-1
Schmelze-Fließrate 2.16kg 190°C Schmelze-Fließrate 2.16kg 190°C			
MFR [g/10min] MFR	4.5	g/10min	ISO 1133
Shorehärteprüfung Shorehärteprüfung			
Shore D Shore D	47		ISO 7691-1

## Disclaimer

Die Materialkennwerte werden an internen Pöppelmann- Prüfkörpern ermittelt. Die Angaben beruhen auf unseren derzeitigen Erfahrungen und Erkenntnissen. Sie befreien den Anwender wegen der Fülle möglicher Einflüsse nicht von eigenen Prüfungen und Versuchen. Eine Garantie bestimmter Eigenschaften oder die Eignung eines Produkts für bestimmte Einsatzzwecke kann aus unseren Angaben nicht abgeleitet werden.

The material properties are determined on internal Pöppelmann test specimens. The information is based on our current experience and knowledge. They do not relieve the user of their own tests and trials because of the abundance of possible influences. A guarantee of certain properties or the suitability of a product for certain purposes can not be derived from our information.